

Product Bulletin

GF 235

MotoMark™ 4.0 mil “GRIP” Matte White Vinyl Special “High Grip - High Bond” Adhesive

GF 235 MotoMark™ 4.0 mil “GRIP” is specially formulated premium flexible matte white PVC film. This film has a unique “High Bond” acrylic pressure sensitive adhesive with a 90# layflat liner. The adhesive is formulated for the powersport graphic and decal markets. **GF 235 MotoMark™** can be printed on a variety of solvent-based, latex, UV and thermal printers that are commonly used in wide format. This product may also be printed on using other printing processes such as UV screen and UV curable offset but must be tested before production.

Applications

GF 235 MotoMark™ is designed for applications where a flexible premium film with special high bond adhesion is required. **GF 235 MotoMark™** is recommended for applications such as, Quads, Snowmobiles, Motocross, Powersport Vehicles, Helmets, and Carts. Testing is always suggested before application.

** Recommended to use **GF 238 MotoMark™** 12mil “ARMOR” Gloss Clear UV overlamine. This will add ultimate protection, performance and durability to the graphic or decal.*

Thickness

Film 4.0 mils.
Adhesive 1.8 to 2.2 mils.
Liner 6.7 mils.
(Thickness variance +/- 10%)

Dimensional Stability Temperature Ranges

Good
Minimum application temperature +40°F.
Service temperature -40°F to +180°F.

Expected Exterior Exposure

5 Years. Under normal exposure conditions

Adhesion

To stainless steel 64 oz/in.
PSTC-101 Method A with 24 hr. dwell at 70°F and 50% relative humidity.
Typical values. Individual values may vary. Test thoroughly before production.

Water Resistance Humidity Resistance Solvent Resistance Storage Stability

Excellent
Excellent
Excellent
Six months shelf life when stored at 70°F and 50% relative humidity.

Product Codes

235-24 (24” x 150’ roll) **235-30 (30” x 150’ roll)**
235-54 (54” x 150’ roll) **235-60 (60” x 150” roll)**

Recommendations

Completely evaporate inkjet solvents before application. Failure to do so may facilitate solvent penetration resulting in vinyl degradation. Always thoroughly test this product to confirm that it meets your requirements. Proper surface preparation requires cleaning with alcohol or acetone to clean and remove contaminants before application. Failure to prepare the surface can cause premature failure of the graphic or decal.

GF 235 is a permanent adhesive system. Removing and repositioning are not characteristics of this adhesive system. The above recommendations of this films use do not suggest or constitute a verbal or written guaranty or warranty by the manufacture or its dealers of this product. Individual purchasers or users shall be responsible for determining the materials suitability as well as its intended use and application.



Manufacturers of
Pressure Sensitive Films

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537
Web Site: www.generalformulations.com • e-mail: info@generalformulations.com

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.